



TOWNSEND CHEMICALS PTY LTD

ABN 26 005 074 073

TEL: (61 3) 9793 6000

FAX: (61 3) 9794 0723

Email: customerservice@townsendchem.com.au

Web: www.townsendchem.com.au

RE-ADD®

URETHANE ADDUCTS

Available in a range of solution viscosities to suit your processing requirements

Grade	Viscosity 15% in MEK	Bond Strength (N/mm)	Heat Resistance (mm), 1kg @ 90°C	Tack Time	Suitable Solvents
RE-ADD 128L	150cP @ 25°C	3.0	Crosslinked 2.0	1-3 Hours	Ketones, Esters THF & DMF
RE-ADD 128M	500cP @ 25°C	3.0	Crosslinked 2.0	1-3 Hours	Ketones, Esters THF & DMF
RE-ADD 128H	2200cP @ 25°C	3.0	Crosslinked 2.0	1-3 Hours	Ketones, Esters THF & DMF
Use as part of a 2 pack adhesives formulation in applications such as shoe adhesives					
RE-ADD 94007M	1000cP @ 25°C	6.1	Uncrosslinked 4.5	10-30 Minutes	Ketones, Esters THF & DMF
Fast crystallising adhesive that can be used without the need for crosslinking					
RE-ADD 314	250cP @ 25°C	N/Av	N/Av	N/Av	MEK
Developed as a low viscosity binder for ferromagnetic particles					
RE-ADD 4008	500cP @ 25°C	4.5	Crosslinked 1.0	0-20 Minutes	Ketones, Esters THF & DMF
Fast crystallising grade suitable for laminating adhesive and shoe adhesive					
RE-ADD 94023	500cP @ 25°C	2.3	Crosslinked 1.0	3-6 Hours	Ketones, Esters THF & DMF
Slow crystallising grade that is suitable for a range of substrates, making it suitable for shoe adhesives					

❖ These are typical properties and should not be used for establishing specifications

- For individual data sheets or information on other available grades, please contact our Customer Service customerservice@townsendchem.com.au

Except as provided above, all expressed and applied warranties, guarantees and conditions said to arise in respect of information supplied by Townsend Chemicals Pty.Ltd. or otherwise under statute or general law as to merchantability, description, quality, suitability or fitness of the goods for any purpose or as to design, assembly, installation, materials or workmanship or otherwise are hereby expressly excluded and Townsend Chemicals Pty.Ltd shall not be liable for physical or financial injury, loss or damage or for consequential loss or damage of any kind arising out of the supply, preparation, production, installation, performance or operation of the goods or arising out of Townsend Chemicals Pty.Ltd.'s negligence or in any way whatsoever. The liability of Townsend Chemicals Pty.Ltd. for a breach of a condition or warranty implied by Div.2 of Pt. V of the trade practices Act 1974 is not excluded or restricted but is (other than S 69) hereby limited to : (a) the replacement of the goods or the supply of equivalent goods.(b) the repair of goods. (c) the payment of the cost of replacing the goods or of acquiring equivalent goods. (d) the payment of the cost of having the goods repaired. Freedom from patent rights must not be assumed.