



TOWNSEND CHEMICALS PTY LTD

ABN 26 005 074 073

TEL: (61 3) 9793 6000

FAX: (61 3) 9794 0723

Email: customerservice@townsendchem.com.au

Web: www.townsendchem.com.au

RE-PLAS®

POLYMERIC PLASTICISERS

RE-PLAS Plasticisers are used to make PVC, rubber and a range of other resins more flexible.

Grade	Viscosity	Acid Value (mg KOH/g)	Hydroxyl Value (mg KOH/g)	Food Contact Status
RE-PLAS 195	1950cP @ 25°C	1.0	21.5	Suitable #
Medium viscosity polymeric plasticiser with good resistance to extraction by oils and fats. Applications include, hose, belt and film.				
RE-PLAS 208	22cSt @ 25°C	1.2	1.5	Not Suitable
Low viscosity plasticiser for use in wire cable and rubber compounds				
RE-PLAS 210	13cSt @ 25°C	0.3	1.5	Suitable #
Low viscosity plasticiser that imparts excellent low temperature flexibility in PVC and rubber compounds				
RE-PLAS 333	350cSt @ 25°C	0.6	12.0	Suitable #
Low viscosity, easy to process polymeric plasticiser with good permanence				
RE-PLAS 805	850cP @ 25°C	0.5	12.0	Not Suitable
Medium viscosity polymeric plasticiser suitable for PVC processing				
RE-PLAS PPA 150	1100cSt @ 60°C	0.5	50.0	Suitable #
High viscosity polymeric plasticiser with excellent resistance to oil and solvent extraction. This plasticiser can be crosslinked				

- Contact Customer Service for further information on food contact status 22cSt @ 25°C 22cSt @ 25°C 22cSt @ 25°C 22cSt @ 25°C

❖ These are typical properties and should not be used for establishing specifications

- For individual data sheets or information on other available grades, please contact our Customer Service customerservice@townsendchem.com.au

Except as provided above, all expressed and applied warranties, guarantees and conditions said to arise in respect of information supplied by Townsend Chemicals Pty.Ltd. or otherwise under statute or general law as to merchantability, description, quality, suitability or fitness of the goods for any purpose or as to design, assembly, installation, materials or workmanship or otherwise are hereby expressly excluded and Townsend Chemicals Pty.Ltd shall not be liable for physical or financial injury, loss or damage or for consequential loss or damage of any kind arising out of the supply, preparation, production, installation, performance or operation of the goods or arising out of Townsend Chemicals Pty.Ltd.'s negligence or in any way whatsoever. The liability of Townsend Chemicals Pty.Ltd. for a breach of a condition or warranty implied by Div.2 of Pt. V of the trade practices Act 1974 is not excluded or restricted but is (other than S 69) hereby limited to : (a) the replacement of the goods or the supply of equivalent goods.(b) the repair of goods. (c) the payment of the cost of replacing the goods or of acquiring equivalent goods. (d) the payment of the cost of having the goods repaired. Freedom from patent rights must not be assumed.